

Amendments to the Specification:

On page 54, please replace the paragraph beginning on line 11 with the following new paragraph:

Composition solutions were prepared by homogenously mixing 100 parts (by weight, hereinafter the same) of siloxane resins shown in Table 3, 900 parts of 2-heptanone, the acid generators (B) shown in [[Table 1]] Table 3, and 8 mol% of 2-phenylbenzimidazole for the total amount of the acid generator (B).